

Super Natural Wide Body

Direct Pressure Laminate with v-groove

Level of use according to EN 13329:

domestic with heavy use

class 23 / 32 - AC 4

commercial with general use



product quality			
dimension	thickness	8,0 ± 0,50 mm dmax - dmin ≤ 0,50 mm	
	length	1285 ± 0,50 mm	
	width	242,0 ± 0,10 mm bmax - bmin ≤ 0,20 mm	
dimension tolerances			
squareness	EN 13329	≤ 0,20 mm	
straightness	EN 13329	≤ 0,30 mm	
flatness crosswise	EN 13329	concave: ≤ 0,15% convex: ≤ 0,20 %	
flatness length	EN 13329	concave: ≤ 0,50 % convex: ≤ 1,00 %	
gaps between elements	EN 13329	average: ≤ 0,15 mm max: ≤ 0,20 mm	
height difference between elements	EN 13329	average: ≤ 0,10 mm max: ≤ 0,15 mm	
functional + surface tests			
abrasion resistance	EN 13329	AC4 (≥ 4000 rpm)	
impact resistance	EN 13329	IC2	
stain resistance	EN 13329	group 1 + 2	grade 5
		group 3	≥ grade 4
castor chair test	EN 13329	no change in appearance or damage, as defined per EN 425	
thickness swelling	EN 13329	≤ 18%	
light fastness	EN 13329	blue wool scale	≥6
		grey scale	≥4
environmental characteristics			
emission of Formaldehyde		class E1	
physical characteristics			
fire behavior	EN 13501-1	Cfl s1	
slip resistance	EN 13893	technical class DS	